

PRODUCT DATA SHEET

Sika® Unitherm® Steel S-60

Future name: Unitherm® Steel SB-60

Solvent based fire protection coating for steel, fast dry, interior* / exterior
use

DESCRIPTION

Sika® Unitherm® Steel S-60 is a fast drying, thin film fire protection coating system for interior* and exterior structural steel work.

Sika® Unitherm® Steel S-60 is forming a heat insulating layer under the influence of fire and improves the fire resistance of steel parts like columns, girders and framework.

USES

Sika® Unitherm® Steel S-60 may only be used by experienced professionals.

For exterior use on structural steel members like columns, girders and framework which are subjected to weathering, high humidity, maritime environment etc. with a highly effective protection to delay the steel from reaching critical temperatures.

* For interior use on structural steel members like columns, girders and framework as long as there is no demand for national emission schemes, e.g. German AgBB, etc.

Note: With critical situation e.g. frequent formation of condensation and/or heating up of surfaces above + 45°C adequate arrangements should be taken.

No topcoat required for dry environments except for a coloured decorative finish.

CHARACTERISTICS / ADVANTAGES

- Fast drying intumescent coating
- Applicable on steel constructions exposed to weathering, the system meets Type X classification (e.g. exterior conditions)
- Excellent corrosion protection properties according to ISO 12944, corrosivity class C3 (as coating system)
- VOC < 320 g/l
- Preserves the appearance of a steel construction
- Applicable to filigree and complex steel building elements
- Simple application, does not increase static load
- Individual coloration possible with corresponding topcoat, various colour shades in RAL, others available

APPROVALS / CERTIFICATES

Independently fire tested and approved to major European and national standards including:

- EN 13381-8 (ref: ETA 20/1161)
- Solvent based coating for steel protection according to EN 13501-2 and EAD 350402-00-1106, DoP, with CE-mark

PRODUCT INFORMATION

Packaging	Sika® Unitherm® Steel S-60	25 kg net.
	Sika® Unitherm® Thinner	25 l and 5 l
Appearance and colour	White	
Shelf life	18 months	
Storage conditions	In originally sealed containers in a cool and dry environment.	
Density	~1.20 g/cm ³	
Flash point	+ 35°C	
Solid content	~73 ± 3% by volume (according BCF Guidance Method)	

SYSTEM INFORMATION

System	<u>Approved generic primer types:</u> On blast cleaned steel:	a) Short / medium oil alkyd, e.g. Sika® Permacor®-1705 b) 2-pack epoxy, e.g. Sika® Permacor®-2706 EG c) Zinc rich epoxy, e.g. SikaCor® Zinc R d) water dispersed zinc rich epoxy, e) Zinc silicate, e.g. SikaCor® Zinc ZS (+ tiecoat Sika® Permacor®-2706 EG)
	On manually de-rusted steel:	SikaCor® Aktivprimer Rapid or Sika Poxicolor® Primer HE NEW
	On galvanized steel:	Sika® Permacor®-2706 EG
	<u>Intumescent coating:</u>	Sika® Unitherm® Steel S-60
	<u>Without topcoat:</u>	Internal exposure, Type Z1 and Z2
	<u>With topcoat:</u>	Semi-exposed, Type Y and external exposure, Type X
	Please consult the Technical Department for further advice.	
	<u>Topcoats:</u>	
	Sika® Unitherm® Top S produced in RAL colour shades or on request for other colour shades.	
	Interior use, Z1/ Z2 (decorative)	1 x 160 g/m ²
	Exterior use, Type X (exposed to weathering)	2 x 140 g/m ²
	(see separate product data sheet Sika® Unitherm® Top S / Sika® Unitherm® Top S EG).	
	SikaCor® EG-5 produced in RAL colour shades, NCS or on request for other colour shades.	
	C3 High (acc. ISO 12944)	1 x 170 g/m ²
	Exterior use, Type X (exposed to weathering)	1 x 170 g/m ²
	(see separate product data sheet SikaCor® EG-5).	
	Please consult the Technical Department for further advice.	

APPLICATION INFORMATION

Consumption	<p>Example: 1000my dry \approx 1300my to 1400my wet \approx 1670 g/m² \approx 1.370 l/m²</p> <p>The fire rate of Sika® Unitherm® Steel S-60 depends on national standard. See corresponding separate consumption table/diagram. Note: Ratio dry film thickness - wet film thickness varies depending on application method. Furthermore, proper ventilation is recommended.</p>						
Relative air humidity	<p>Max. 80 %, application temperature shall be at least \geq 3 K above dew point. During application and drying of total Sika® Unitherm® coating system including Sika® Unitherm® Top S or SikaCor® EG-5 topcoat as well as transportation special protection measures must be taken against weathering.</p>						
Surface temperature	<p>Object temperature not below + 5°C, to max. + 40°C* * If higher temperatures occur, please consult the Technical department for further assistance.</p>						
Waiting time to overcoating	<p>Sika® Unitherm® Steel S-60 requires a minimum of 24 hours drying prior to application of topcoat Sika® Unitherm® Top S / Sika® Unitherm® Top S EG or SikaCor® EG-5. A complete drying of the fire protection coating prior topcoat application is highly recommended. Through-drying of Sika® Unitherm® Steel S-60 can be checked by 'finger-nail-test'. Prior to further applications possible contaminations must be removed.</p>						
Drying time	<p>Drying / Curing Average drying time at + 23°C:</p> <table><tr><td>Touch-dry</td><td><u>< 1 h</u></td></tr><tr><td>Overcoatable</td><td><u>~4 h</u></td></tr><tr><td>Dry-to-handle</td><td>Depends on the total thickness of Sika® Unitherm® Steel S-60 to be applied</td></tr></table> <p>Different temperature, different relative humidity's and different fire protection coating thicknesses have an influence on drying time.</p>	Touch-dry	<u>< 1 h</u>	Overcoatable	<u>~4 h</u>	Dry-to-handle	Depends on the total thickness of Sika® Unitherm® Steel S-60 to be applied
Touch-dry	<u>< 1 h</u>						
Overcoatable	<u>~4 h</u>						
Dry-to-handle	Depends on the total thickness of Sika® Unitherm® Steel S-60 to be applied						

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Various 'info data sheets' such as primers or repair instructions.

For further information please consult Sherwin-Williams.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Blast cleaned steel:

Blast-cleaning to Sa 2 ½ according to ISO 8501-1. Free from dirt, oil and grease.

Steel with manual de-rusting:

Manual de-rusting (wire brushing or power tool cleaning) according to ISO 8501-1, St. 3

Galvanized steel:

Free from dirt, oil, grease and zinc salts. In case of permanent exposure to submersion and condensation surfaces should be sweep blasted according to ISO 12944-4.

Other surfaces:

Tests should be carried out on the specific surfaces.

For contaminated and weathered surfaces e.g. galvanized or primed areas we recommend to clean with SikaCor® Wash.

Application to multi coating systems e.g. to accommodate requirements according to ISO 12944-5 (e.g. DFT > 250my) are applicable to Sika® Unitherm® Steel S-60. For further information, please consult the Technical Department.

MIXING

Stir thoroughly with slowly turning mechanical stirrer, free of lumps. Addition of thinner is not necessary.

APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. In case of application by roller or brush, additional layers may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to application a trial on site may be useful to ensure the selected application method will provide the requested results.

By brush and roller:

- Material shall be applied undiluted
- Solvent resistant brush or roller must be used

Airless spraying:

- Material shall be applied undiluted
- Airless machine with pressure ratio ≥ 45 : 1
- Screens and filters should be removed
- Hose diameter not below ¾ “
- Nozzle size 0.46 - 0.66 mm (0.019 - 0.027 inch)
- Solvent resistant hoses must be used!

To adjust the material to less professional equipment, dilution up to 3 % with Sika® Unitherm® Thinner is possible.

Dilution up to 3 % still complies with the limits given by the Decopaint directive but the loading per layer is likely to be adjusted.

Note: The Sika® Unitherm® Steel S-60 shall be applied in several coats up to the final dry film thickness required. Wet film thickness max. 400my for first application coat on primer. Wet film thickness approx. 750my for each subsequent application coat is recommended.

CLEANING OF EQUIPMENT

Immediately after use with Sika® Unitherm® Thinner.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sherwin-Williams` products, are given in good faith based on Sherwin-Williams` current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sherwin-Williams` recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product`s suitability for the intended application and purpose. Sherwin-Williams reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sherwin-Williams Coatings
Deutschland GmbH
Rieter Tal
D-71665 Vaihingen / Enz
Phone: +49 (0)7042 109-0
pm.de.info@sherwin.com



PRODUCT DATA SHEET
Sika® Unitherm® Steel S-60
March 2022, Version 01

**SHERWIN
WILLIAMS®**